

Self Regulatory Drug Transport: An Intelligent Drug Delivery System

Transporte autorregulador de fármacos: un sistema inteligente de administración de fármacos

Ashish Jain, Pradeep Kumar Mohanty

School of Pharmacy, LNCT University, Kolar Road Bhopal, M.P., India

<http://dx.doi.org/10.30827/ars.v59i3.7437>

Artículo de revisión Review Article

Correspondencia Correspondence

Ashish Jain
aashish.pharmatech@gmail.com

Financiación Fundings

We have not received any financial support from other source.

Conflicto de interés Competing interest

We declare that we have no conflict of interest

Acknowledgments Agradecimientos

The authors are thankful to the Managements of School of Pharmacy, LNCT University, and Bhopal for their unconditional support in the field of research and developments.

Received: 22.05.2018
Accepted: 25.07.2018

ABSTRACT

Introduction: Main objective of any pharmaceutical scientist is to develop drug delivery system that is safe, effective, stable, having good patient compliance and fulfill the requirements of customers. Lead to a great interest of research to develop the drug delivery system that will enable to supply drug «on-demand» basis. These «stimuli-responsive and intelligent» systems have been designed to deliver the drug on various times or at various sites in the body, according to a stimulus that is either endogenous or externally applied.

Objectives: This paper aim to review various researches in the field of self regulatory drug delivery systems in tabular form so one can utilize these finding for further development of in intelligent drug delivery systems.

Method: Various physicochemical principles and chemical schemes have been applied by researchers to get release pattern of drug as per requirement of body. Such devices can be used for intelligent drug delivery needed for the treatment of many diseases like diabetes.

Results & Discussion: This type of intelligent system firstly sense the signals caused by diseaseà judge the magnitude of signalsà and then release the drug in direct response.

Conclusion: In this article we have discuss various innovations in the field of self regulatory drug delivery Systems and suggest that here is a lot of research scope in this field.

Keywords: Intelligent Drug delivery System; Self Regulatory; Drug Delivery Systems.

RESUMEN

Introducción: El objetivo principal de cualquier científico farmacéutico es desarrollar un sistema de administración de fármacos que sea seguro, efectivo, estable, que cumpla con los requisitos del paciente y cumpla con los requisitos de los clientes. Llevar a un gran interés de investigación para desarrollar el sistema de entrega de medicamentos que permitirá suministrar medicamentos «a demanda». Estos sistemas «sensibles a estímulos e inteligentes» han sido diseñados para administrar el fármaco en varios momentos o en varios sitios en el cuerpo, de acuerdo con un estímulo endógeno o aplicado externamente.

Objetivos: Este artículo tiene como objetivo revisar diversas investigaciones en el campo de los sistemas autorreguladores de administración de fármacos en forma tabular para que uno pueda utilizar estos hallazgos para un mayor desarrollo de sistemas inteligentes de administración de fármacos.

Método: Los investigadores han aplicado varios principios fisicoquímicos y esquemas químicos para obtener el patrón de liberación del fármaco según las necesidades del cuerpo. Dichos dispositivos se pueden usar para la administración inteligente de medicamentos necesarios para el tratamiento de muchas enfermedades, como la diabetes.

Resultados y discusión: Este tipo de sistema inteligente primero detecta las señales causadas por la enfermedad, juzga la magnitud de las señales y luego libera la droga en respuesta directa.

Conclusión: En este artículo, hemos discutido varias innovaciones en el campo de los sistemas autorreguladores de administración de fármacos y sugerimos que aquí hay mucho campo de investigación en este campo.

Palabras clave: Sistema inteligente de administración de fármacos; Autorregulador.



LICENSE 3.0 UNPORTED.

INTRODUCTION

As the traditional drug delivery systems (DDSs) often associated with many side effects, there is always a requirement of approaches to develop new formulations for transporting medicine at required level when it is needed. This type of on-demand basis drug delivery is also called smart drug delivery or intelligent drug delivery. These novel techniques enhance the therapeutic values and also reduce various side effects. In comparison to the conventional DDSs, the smart controlled DDSs can effectively reduce the dosage frequency, while maintaining the drug concentration in targeted organs/tissues for a longer period of time. In this sense, the controlled DDSs provide broad insights and fascinating properties for decreasing drug concentration fluctuation, reducing drug toxicities and improving therapeutic efficacy.¹

This new class of intelligent or smart and responsive delivery systems is designed to perform various functions like detection, isolation and/or release of therapeutic agent for

the treatment of various diseases. Intelligent drug delivery systems are mostly based on stimuli-responsive polymers which sense a change in a specific variable and activate the delivery; this phenomenon being reversible. A large number of materials such as polymers, lipids and inorganic materials, have been developed to control the drug release in this manner to create a smart drug delivery system.²⁻⁷

Benefits of intelligent drug delivery systems

1. Intelligent drug delivery systems are capable to deliver the drug as per the physiological needs.
2. This system helps to maintain the plasma drug concentration within the therapeutic range.
3. Localized delivery of drug to a particular compartment (targeted site) can be achieved.
4. Preserve the drugs that are rapidly destroyed, enhance the stability.
5. Improve patient compliance.

MATERIAL AND METHODS

How it work??

It senses the signal caused by disease

(SENSOR FUNCTION)



Judges the magnitude of signal

(PROCESSOR FUNCTION)



Then act to release the drug in direct response

(EFFECTOR FUNCTION)




Figure 1: Intelligent drug delivery system

TYPE OF INTELLIGENT DRUG DELIVERY SYSTEMS³⁻⁷

Broadly classify in two categories

- 1. Open-loop system:** These are also known as externally controlled system or pulsatile systems. These system employed external triggers to deliver the drug such as magnet, temperature, ultrasound, electric effects etc.
- 2. Close-loop system.** These are also known as self regulated drug delivery systems or responsive systems. Rate of drug release controlled by feedback information without external intervention. These are uses various approached such as pH-responsive, glucose responsive, thermo-sensitive, urea responsive, inflammation sensitive etc.

Some are discussed below:

a. pH-responsive system

In this type of system pH use as a trigger to release the drug. Alteration in pH of the environment will cause swelling or de-swelling of the polymer. pH-responsive carriers is used to sense the pH at different region of body such as stomach (pH \approx 2) and intestinal tract (pH \approx 7).⁸⁻¹¹

b. Redox-responsive system

Oxidation-reduction responsive system have gained huge interest for disease therapy.^{12,13} The redox potential in microenvironments is multivariate in different tissues, which can be exploited to design redox-sensitive delivery systems. The design and fabrication of nanoparticles responsive to Glutathione can be a promising approach for targeting drug delivery.¹⁴

c. Enzyme-responsive system

Enzymes used as triggers in the design of smart drug delivery systems and gain attention due to its its unique superiorities, such as substrate specificity and high selectivity¹⁵⁻¹⁸. Since enzymes (such as glycosidases, lipase, phospholipases or proteases) are related to almost all the biological and metabolic process, they can be use to get enzyme-mediated drug release¹⁷.

d. Thermo responsive system

Temperature is one of the most suitable and efficient factors to control the drug release compared with other stimuli.¹⁹⁻²¹ Poly (acrylamide) gels swell with increasing temperature, while poly(N-alkyl substituted acrylamide) gels deswell. Usually, disease state body temperature raised as compared to normal state some conditions, such as inflammation and tumors, have higher temperatures than normal

tissues²². By use of this temperature difference between cancer tissues and normal tissues, smart drug delivery can be use to enhance their drug release in tumors^{23,24}. Another temperature- responsive strategy is that the tumor site could be heated by external triggers (Ultra sound, magnetic field, etc.) to improve the drug release within the tumor vasculature microenvironment.²⁵

e. Light, magnetic, and ultra sound responsive

Photo sensitive carriers are used to design light responsive drug delivery system and the drug release accompanied at desired site by external light illumination. In the magnetic and ultra sound responsive drug delivery system external magnetic field and ultra sound is used respectively to trigger drug molecules at targeted site.²⁶

f. Other responsive systems

Glucose and other Saccharide Sensitive Systems, electro-responsive systems, Inflammation Responsive Systems, Electrically Regulated Systems, Urea Responsive Delivery Systems, Morphine Triggered Naltrexone Delivery Systems, System Utilizing Antibody Interactions, System Utilizing Chelation have also been employed to control the release of drug from smart system. Dual stimuli-responsive DDSs are most common systems and have been investigated, such as thermo- and pH- responsive systems, redox- and pH- responsive systems thermo- and light- responsive systems, ultrasonic and magnetic responsive systems.²⁷⁻³⁹

Recent advancements

Insulin Pump

The ultimate goal for diabetes mellitus is to control the blood glucose level by insulin delivery and minimized the long-term diabetic complications. Currently main therapy is to administered insulin through subcutaneous injection for diabetes patients. Two or three injections are required a day to maintain the normal blood glucose level. Because this method is burdensome and invasive to living organisms, the patient's situation would not be good regarding the quality of life. Therefore, an electrical and mechanical controlled insulin pump that injects insulin automatically into the bloodstream has been developed. An insulin pump constructed with polymer materials has been studied. Many researchers working on deliver insulin by smart device.

Gluco Watch

A GlucoWatch™ biographer is non-invasive, watch like device that measures glucose. A plastic part of Gluco watch that snaps into the biographer and sticks to the skin. Auto-

matic reading every 10 min up to 13 hrs is taken by it. Gluco watch presently takes the lead among user-friendly techniques aimed at glucose monitoring. This system is based upon the principle of reverse iontophoresis.

Stimuli-responsive drug-delivery systems in clinical trials:

- **a. AuroShell:** Thermosensitive gold nanoshell are prepared by Nanospectra Biosciences for Intracranial tumors⁴⁰.
- **b. Opaxio:** Enzyme-activated polymeric NP are prepared by Cell Therapeutics, Inc. for treatment of Ovarian cancer.⁴¹
- **c. ThermoDox:** Thermosensitive liposomal doxorubicin are prepared by Celsion Corporation are useful in Breast cancer and primary liver cancer.⁴²
- **d. NanoTherm:** Magnetic sensitive iron oxide NPs are prepared by MagForce Nanotechnologies AG for Glioblastoma, prostata cancer, eosophageal cancer and pancreatic cancer.⁴³

RESULTS AND DISCUSSION

Current researches in the field of intelligent drug delivery summarized here in tabular form:

Researchers / Year	Title of work	Work summary and Findings
Li <i>et al.</i> , (2018)	One-Step Preparation of pH-Responsive Polymeric Nanogels as Intelligent Drug Delivery Systems for Tumor Therapy	In this work, pH-responsive polypeptide-based nanogels are reported as potential drug delivery systems. At pH 7.4, MPEG- <i>b</i> -PN-LG nanogels exhibit high stabilities with hydrophobic inner cores, which allow encapsulation of hydrophobic therapeutic agents. Under tumoral acidic environments (pH ~6.4), the cleavage of benzoic imine bonds induces the destruction of MPEG- <i>b</i> -PNLG nanogels and leads to rapid release of their payloads. Doxorubicin is used as a model drug to evaluate drug encapsulation and release. ⁴⁴
Zhang <i>et al.</i> , (2018)	Mesoporous silica nanoparticle-based intelligent drug delivery system for bienzyme-responsive tumour targeting and controlled release	This paper proposes a novel type of multifunctional envelope-type mesoporous silica nanoparticle (MSN) to achieve cancer cell targeting and drug-controlled release. In this system, MSNs were first modified by active targeting moiety hyaluronic acid (HA) for breast cancer cell targeting and hyaluronidases (Hyal)-induced intracellular drug release. Then gelatin, a proteinaceous biopolymer, was grafted onto the MSNs to form a capping layer via glutaraldehyde-mediated cross-linking. This system presents successful bienzyme-responsive targeting drug delivery in an optimal fashion and provides potential applications for targeted cancer therapy. ⁴⁵
Zhao <i>et al.</i> , (2018)	An intelligent dual stimuli-responsive photosensitizer delivery system with O ₂ -supplying for efficient photodynamic therapy	In this paper, a new type of biocompatible multifunctional photosensitizer delivery system was fabricated to relieve tumor hypoxia and improve the efficacy of PDT. ⁴⁶
Li <i>et al.</i> , (2018)	Dual-responsive drug delivery systems prepared by blend electrospinning	Temperature and pH dual-responsive drug delivery systems prepared by the thermosensitive polymer poly(N-isopropylacrylamide) (PNIPAAm) by polymerization. It was then co-dissolved with the pH-sensitive polymer Eudragit® L100-55 (EL100-55) and processed into fibers using electrospinning. Ketoprofen, a model drug, was also incorporated into the composite fibers, and fibers based on a single polymer additionally prepared. ⁴⁷
Kumar <i>et al.</i> , (2017)	Mesoporous silica nanoparticle based enzyme responsive system for colon specific drug delivery through guar gum capping	Herein, Researchers have developed a mesoporous silica nanoparticle (MSN) based enzyme responsive materials for colon specific drug delivery. They have utilized guar gum, a natural carbohydrate polymer as a capping layer to contain a model drug, such as 5-fluorouracil (5FU) within the mesoporous channels of MSN. The drug loaded GG-MSN system also demonstrated near perfect 'zero release' property in absence of enzymes in different simulated conditions of the gastrointestinal tract. ⁴⁸
Yang <i>et al.</i> , (2016)	Glucose and magnetic-responsive approach toward in situ nitric oxide bubbles controlled generation for hyperglycemia theranostics.	Magnetic microvesicles with glucose oxidase designed as a novel theranostic approach for restoring glucose homeostasis and spatiotemporally control nitric oxide release for maintaining good overall diabetic health. ⁴⁹

Researchers / Year	Title of work	Work summary and Findings
Stumpel <i>et al.</i> , (2015)	Stimuli-Responsive Materials Based on Interpenetrating Polymer Liquid Crystal Hydrogels	Stimuli-responsive materials based on interpenetrating liquid crystal-hydrogel polymer networks are fabricated. These materials consist of a cholesteric liquid crystalline network that reflects color and an interwoven poly(acrylic acid) network that provides a humidity and pH response. The volume change in the cross-linked hydrogel polymer results in a dimensional alteration in the cholesteric network as well, which, in turn, leads to a color change yielding a dual-responsive photonic material. ⁷
Yu <i>et al.</i> , (2015)	Reversal of doxorubicin resistance in breast cancer by mitochondria-targeted pH-responsive micelles.	Researchers reported an effective approach to overcome doxorubicin (DOX) resistance in MCF-7/ADR breast cancer using DOX-loaded pH-responsive micelles. The micelles were prepared from a pH-responsive diblock copolymer, poly(ethylene glycol)-block-poly(2-(diisopropylamino)ethyl methacrylate) (PEG- <i>b</i> -PDPA), and a vitamin E derivative (D- α -tocopheryl polyethylene glycol 1000 succinate, TPGS) (denoted as PDPA/TPGS micelles). ²⁴
Nguyen <i>et al.</i> , (2015)	Enzyme-Responsive Nanoparticles for Targeted Accumulation and Prolonged Retention in Heart Tissue after Myocardial Infarction.	Enzyme-responsive peptide-polymer amphiphiles are assembled as spherical micellar nanoparticles, and undergo a morphological transition from spherical-shaped, discrete materials to network-like assemblies when acted upon by matrix metalloproteinases (MMP-2 and MMP-9), which are up-regulated in heart tissue post-myocardial infarction. ³⁶
Callmann <i>et al.</i> , (2015)	Therapeutic Enzyme-Responsive Nanoparticles for Targeted Delivery and Accumulation in Tumors	An enzyme responsive, paclitaxel loaded nanoparticle is described and assessed in vivo in a human fibrosarcoma murine xenograft. This work represents a proof-of-concept study demonstrating the utility of enzyme-responsive nanoscale drug carriers capable of targeted accumulation and retention in tumor tissue in response to overexpressed endogenous enzymes. ¹⁶
Paris <i>et al.</i> , (2015)	Polymer-Grafted Mesoporous Silica Nanoparticles as Ultrasound-Responsive Drug Carriers.	A new ultrasound-responsive system based on mesoporous silica nanoparticles was developed for biomedical applications, grafting a copolymer on their surface that acts as gate keeper of the pores. Upon ultrasound irradiation, the sensitive polymer changes its hydrophobicity and, therefore, its conformation toward coil-like opening the gates and releasing the drug. ⁵⁰
Curcio <i>et al.</i> , (2015)	On demand delivery of ionic drugs from electro-responsive CNT hybrid films.	Electro-responsive hybrid hydrogel films were prepared by UV-induced polymerization of Acrylamide and <i>N,N'</i> -ethylene bisacrylamide to be applied for the on/off delivery of therapeutics. Swelling behaviour and drug release profiles were evaluated in the presence of an external applied electric voltage and mathematically modelled. The application of an external electric voltage resulted in a faster release of anionic drugs, while a slower release was recorded for cationic drugs. ³²
Alvarez-Lorenzo <i>et al.</i> , (2014)	Smart drug delivery systems: from fundamentals to the clinic	This review offers a critical overview of therapeutically-interesting stimuli to trigger drug release and the evolution of responsive materials suitable as functional excipients, illustrated with recent examples of formulations in clinical trials or already commercially available, which can provide a perspective on the current state of the art on smart drug delivery systems. ⁵¹
Liu <i>et al.</i> , (2014)	pH-Sensitive nano-systems for drug delivery in cancer therapy.	Paper showed that pH-Sensitive nano-systems have now been developed in which drug release is specifically triggered by the acidic tumor environment. Studies have demonstrated that novel pH-sensitive drug delivery systems are capable of improving the efficiency of cancer treatment. A number of these have been translated from bench to clinical application and have been approved by the food and drug administration for treatment of various cancerous diseases. ⁸

Researchers / Year	Title of work	Work summary and Findings
Ganesh <i>et al.</i> , (2014)	Smart functional polymers-a new route towards creating a sustainable environment.	This review indicated recent developments in the area of smart functional polymers with a focus on various (physical, chemical and biological) stimuli responsive systems and their applications. Furthermore, article also provides useful insights and in-depth analysis on the feasibility of utilizing stimuli responsive polymeric materials/composites in anti-fouling and water harvesting applications which hold tremendous potential to create a sustainable environment. ⁹
Torchilin <i>et al.</i> , (2014)	Multifunctional, stimuli-sensitive nanoparticulate systems for drug delivery	Here, researchers highlighted recent developments with multifunctional and stimuli-sensitive novel drug delivery systems and their therapeutic potential for diseases including cancer, cardiovascular diseases and infectious diseases. ²⁵
Chiang <i>et al.</i> , (2014)	pH-responsive polymer-liposomes for intracellular drug delivery and tumor extracellular matrix switched-on targeted cancer therapy	In this study, ECM-targeting liposomes were completely investigated their pH-responsibility, drug releasing behaviors, anticancer efficiencies and the time-dependent organ distribution and toxic effects. ⁵²
Mura <i>et al.</i> , (2013)	Stimuli-responsive nanocarriers for drug delivery	In this Review, researchers have discussed recent advances in the design of nanoscale stimuli-responsive systems that are able to control drug biodistribution in response to specific stimuli, either exogenous (variations in temperature, magnetic field, ultrasound intensity, light or electric pulses) or endogenous (changes in pH, enzyme concentration or redox gradients). ¹²
Kelley <i>et al.</i> , (2013)	Stimuli-responsive copolymer solution and surface assemblies for biomedical applications.	In this review, researchers have discuss several methods that have been employed to synthesize self-assembling and stimuli-responsive copolymers for biomedical applications, and we identify common themes in the response mechanisms among the targeted stimuli. Additionally, we highlight parallels between the chemistries used for generating solution assemblies and those employed for creating copolymer surfaces. ⁵³
Cheng <i>et al.</i> , (2013)	Dual and multi-stimuli responsive polymeric nanoparticles for programmed site-specific drug delivery	Researchers studied novel dual and multi-stimuli responsive polymeric nanoparticles that respond to a combination of two or more signals such as pH/temperature, pH/redox, pH/magnetic field, temperature/reduction, double pH, pH and diols, temperature/magnetic field, temperature/enzyme, temperature/pH/redox, temperature/pH/magnetic, pH/redox/magnetic, temperature/redox/guest molecules, and temperature/pH/guest molecules have recently been developed. These dual and multi-stimuli responsive polymeric nanoparticles have shown unprecedented control over drug delivery and release leading to superior in vitro and/or in vivo anti-cancer efficacy. ⁵⁴
Duan <i>et al.</i> , (2013)	Smart pH-sensitive and temporal-controlled polymeric micelles for effective combination therapy of doxorubicin and disulfiram	A smart pH-sensitive polymeric micelles system with high drug loading and precise drug ratio was designed and prepared by conjugating doxorubicin (DOX) to poly(styrene-co-maleic anhydride) (SMA) derivative with adipic dihydrazide (ADH) through a acid-cleavable hydrazone bond, and then encapsulating disulfiram (DSF), a P-gp inhibitor as well as an apoptosis inducer, into the micelles formed by the self-assembly of SMA-ADH-DOX (SAD) conjugate. The pH-sensitive polymeric micelles system enabled a temporal release of two drugs ⁵⁵
Pan <i>et al.</i> , (2012)	Redox/pH dual stimuli-responsive biodegradable nanohydrogels with varying responses to dithiothreitol and glutathione for controlled drug release	A new type of redox/pH dual stimuli-responsive poly(methacrylic acid) (PMAA)-based nanohydrogels was prepared from methacrylic acid and N,N-bis(acryloyl)cystamine crosslinker via distillation-precipitation polymerization. These nanohydrogels possess many favorable traits, such as excellent biocompatibility and biodegradability, minimal drug release under an extracellular condition (non-reductive), adequate drug loading capacity, and rapid drug release. ⁵⁶

Researchers / Year	Title of work	Work summary and Findings
Mo <i>et al.</i> , (2012)	Multistage pH-Responsive Liposomes for Mitochondrial-Targeted Anticancer Drug Delivery.	Zwitterionic oligopeptide liposomes (HHG2C ₁₈ -L) containing a smart lipid (1,5-dioctadecyl-L-glutamyl 2-histidyl-hexahydrobenzoic acid, HHG2C ₁₈) are developed to overcome the barriers faced by anticancer drugs on the route from the site of injection into the body to the final antitumor target within transport steps with multiple physiological and biological barriers. HHG2C ₁₈ -L show the multistage pH-responsive to the tumor cell (mitochondria in this case). ⁵⁷
Leung <i>et al.</i> , (2012)	Light-activated content release from liposomes	This review focuses on the development of liposome-based functional materials, where payload release is activated by light. Methods of sensitizing liposomes to light have progressed from the use of organic molecular moieties to the use of metallic plasmon resonant structures. This development has facilitated application of near infrared light for activation, which is preferred for its deep penetration and low phototoxicity in biological tissues. ⁵⁸
Yudina <i>et al.</i> , (2011)	Ultrasound-mediated intracellular drug delivery using microbubbles and temperature-sensitive liposomes.	In this study, ECM-targeting liposomes were completely investigated their pH-responsibility, drug releasing behaviors, anticancer efficiencies and the time-dependent organ distribution and toxic effects. Experimental results indicate that ECM-targeting liposomes showed rapid drug releasing profiles in acidic conditions. ⁵⁹
Delcea <i>et al.</i> , (2011)	Stimuli-responsive LbL capsules and nanoshells for drug delivery	Review of basic principles and recent developments in the area of stimuli responsive polymeric capsules and nanoshells formed via layer-by-layer (LbL) is presented. The stimuli can be logically divided into three categories: physical (light, electric, magnetic, ultrasound, mechanical, and temperature), chemical (pH, ionic strength, solvent, and electrochemical) and biological (enzymes and receptors). Using these stimuli, numerous functionalities of nanoshells have been demonstrated. ⁶⁰
Zhao <i>et al.</i> , (2011)	PEGylated thermo-sensitive poly (amidoamine) dendritic drug delivery systems	Researchers engineered PEGylated thermo-sensitive dendritic derivatives and investigated their temperature sensitivity and drug release behaviour therein. ²⁴
Wu <i>et al.</i> , (2011)	Organization of glucose-responsive systems and their properties	In this review, researchers described various glucose-responsive systems and their properties and their future prospectus. ²⁸
Yun <i>et al.</i> , (2011)	Electro-responsive transdermal drug delivery behavior of PVA/PAA/MW-CNT nanofibers.	The electro-responsive transdermal drug delivery system was prepared by electrospinning of poly(vinyl alcohol)/poly(acrylic acid)/multi-walled carbon nanotubes (MWCNTs) nanocomposites. The conductivity of nanofibers increased by increasing the content of MWCNTs and performing oxyfluorination with higher oxygen content. ³⁰
Liu <i>et al.</i> , (2010)	Magnetically sensitive alginate-templated polyelectrolyte multilayer microcapsules for controlled release of doxorubicin	Magnetically sensitive alginate-templated polyelectrolyte multilayer microcapsules were successfully synthesized by a novel process combining emulsification and layer-by-layer self-assembly techniques. The in vitro release behavior under a high-frequency magnetic field (HFMF) indicated that the applied HFMF accelerated significantly the drug release from the microcapsules, which might be related to the microcapsules' magnetic properties. ⁶¹
Gao <i>et al.</i> , (2010)	pH-responsive nanoparticles for drug delivery	Nanoparticles whose cores become soluble or change their structures to release the carried drugs at the tumor extracellular pH or lysosomal pH have been developed for fast drug release into the extracellular fluid or cytosol. Such pH-responsive nanoparticles have therapeutic advantages over the conventional pH-insensitive counterpart. ¹⁰

Researchers / Year	Title of work	Work summary and Findings
Patel <i>et al.</i> , (2008)	Enzyme-responsive snap-top covered silica nanocontainers	Mesoporous silica nanoparticles, capable of storing a payload of small molecules and releasing it following specific catalytic activation by an esterase, have been designed and fabricated. The storage and release of the payload is controlled by the presence of rotaxanes. ⁶²
Zhang <i>et al.</i> , (2007)	Thermo and pH Dual-Responsive Nanoparticles for Anti-Cancer Drug Delivery	Thermo and pH dual-responsive nanoparticles for an anti-cancer drug were prepared. These nanoparticles aggregated at body temperature under a slightly acidic pH of 6.9 (see figure), and a faster drug release was found to be associated with higher temperature and lower pH, both of which are advantageous for tumor-targeted anti-cancer drug delivery. ³³
Murdan <i>et al.</i> , (2003)	Electro-responsive drug delivery from hydrogels.	Electrically-responsive drug release is influenced by a number of factors such as the nature of the drug and of the gel, the experimental set-up, magnitude of the electric field etc. In this paper, electrically-responsive hydrogels, response of gels to an electric field and electrically-stimulated drug release are discussed. ⁶³

CONCLUSION

Intelligent drug deliver means deliver of drug to selectively to targeted cells and tissues while leaving other healthy parts of the body untouched. Although research working on many areas to improve drug delivery to targeted site and therefore drug delivery systems gained wide attention in biomedical research due to their potential to significantly reduce the side effects of drugs and control the concentration and location of active drugs released in the body over long periods of time. Clearly new strategies for preparing drug delivery systems are capable of selectively releasing drug at targeted site will help improve many of the current problems in drug therapy.

REFERENCES

- Liu D, Yang F, Xiong F, Gu N. The Smart Drug Delivery System and Its Clinical Potential. *Theranostics*. 2016;6(9):1306-1323. DOI: 10.7150/thno.14858
- Annabi N, Tamayol A, Uquillas JA, Akbari M, Bertassoni LE, Cha C, et al. 25th anniversary article: rational design and applications of hydrogels in regenerative medicine. *Adv Mater*. 2014;26:85-124. DOI: 10.1002/adma.201303233
- Chang HI, Yeh MK. Clinical development of liposome-based drugs: formulation, characterization, and therapeutic efficacy. *Int J Nanomedicine*. 2012;7:49-60. DOI: 10.2147/ijn.s26766
- Kumari A, Yadav SK, Yadav SC. Biodegradable polymeric nanoparticles based drug delivery systems. *Coll Surfaces B Biointerfaces*. 2010;75:1-18. DOI: 10.1016/j.colsurfb.2009.09.001
- Rossi F, Ferrari R, Castiglione F, Mele A, Perale G, Moscatelli D. Polymer hydrogel functionalized with biodegradable nanoparticles as composite system for controlled drug delivery. *Nanotechnology*. 2014;26:015602. DOI: 10.1088/0957-4484/26/1/015602
- Shimoni O, Postma A, Yan Y, Scott AM, Heath JK, Nice EC. Macromolecule functionalization of disulfide-bonded polymer hydrogel capsules and cancer cell targeting. *ACS Nano*. 2012;6:1463-72. DOI: 10.1021/nn204319b
- Stumpel JE, Gil ER, Spoelstra AB, Bastiaansen CW, Broer DJ, Schenning AP. Stimuli-Responsive Materials Based on Interpenetrating Polymer Liquid Crystal Hydrogels. *Adv Fun Mater*. 2015;25:3314-20. DOI: 10.1002/adfm.201500745
- Liu J, Huang Y, Kumar A, Tan A, Jin S, Mozhi A, et al. pH-Sensitive nano-systems for drug delivery in cancer therapy. *Bio Adv*. 2014;32:693-710. DOI: 10.1016/j.biotechadv.2013.11.009
- Ganesh VA, Baji A, Ramakrishna S. Smart functional polymers-a new route towards creating a sustainable environment. *RSC Adv*. 2014;4:53352-64. DOI: 10.1039/c4ra10631h
- Gao W, Chan JM, Farokhzad OC. pH-responsive nanoparticles for drug delivery. *Mol Pharm*. 2010;7:1913-20. DOI: 10.1021/mp100253e
- Yu P, Yu H, Guo C, Cui Z, Chen X, Yin Q, et al. Reversal of doxorubicin resistance in breast cancer by mitochondria-targeted pH-responsive micelles. *Acta Biomater*. 2015;14:115-24. DOI: 10.1016/j.actbio.2014.12.001
- Mura S, Nicolas J, Couvreur P. Stimuli-responsive nanocarriers for drug delivery. *Nat Mater*. 2013;12:991-1003. DOI: 10.1038/nmat3776
- Huo M, Yuan J, Tao L, Wei Y. Redox-responsive polymers for drug delivery: from molecular design to applications. *Poly Chem*. 2014;5:1519-28. DOI: 10.1039/c3py01192e
- Wang J, Sun X, Mao W, Sun W, Tang J, Sui M, et al. Tumor Redox Heterogeneity-Responsive Prodrug Nanocapsules

- for Cancer Chemotherapy. *Adv Mater.* 2013;25:3670-6. DOI: 10.1002/adma.201300929
15. Nguyen MM, Carlini AS, Chien MP, Sonnenberg S, Luo C, Braden RL, et al. Enzyme-Responsive Nanoparticles for Targeted Accumulation and Prolonged Retention in Heart Tissue after Myocardial Infarction. *Adv Mater.* 2015;27:5547-52. DOI: 10.1002/adma.201502003
 16. Callmann CE, Barback CV, Thompson MP, Hall DJ, Mattrey RF, Gianneschi NC. Therapeutic Enzyme-Responsive Nanoparticles for Targeted Delivery and Accumulation in Tumors. *Adv Mater.* 2015;27:4611-5. DOI: 10.1002/adma.201501803
 17. De La Rica R, Aili D, Stevens MM. Enzyme-responsive nanoparticles for drug release and diagnostics. *Adv Drug Deliv Rev.* 2012;64:967-78. DOI: 10.1016/j.addr.2012.01.002
 18. Lock LL, Tang Z, Keith D, Reyes C, Cui H. Enzyme-Specific Doxorubicin Drug Beacon as Drug-Resistant Theranostic Molecular Probes. *ACS Macro Lett.* 2015;4:552-5. DOI: 10.1021/acsmacrolett.5b00170
 19. Shi Y, van den Dungen ET, Klumperman B, van Nostrum CF, Hennink WE. Reversible Addition-Fragmentation Chain Transfer Synthesis of a Micelle-Forming, Structure Reversible Thermosensitive Diblock Copolymer Based on the N-(2-Hydroxy propyl) Methacrylamide Backbone. *ACS Macro Lett.* 2013;2:403-8. DOI: 10.1021/mz300662b
 20. Shi Y, van Steenberg MJ, Teunissen EA, Novo Ls, Gradmann S, Baldus M, et al. π - π stacking increases the stability and loading capacity of thermosensitive polymeric micelles for chemotherapeutic drugs. *Biomacromolecules.* 2013;14:1826-37. DOI: 10.1021/bm400234c
 21. Shi Y, Cardoso RM, Van Nostrum CF, Hennink WE. Anthracene functionalized thermosensitive and UV-crosslinkable polymeric micelles. *Polym Chem.* 2015;6:2048-53. DOI: 10.1039/c4py01759e
 22. Danhier F, Feron O, Pr at V. To exploit the tumor microenvironment: passive and active tumor targeting of nanocarriers for anti-cancer drug delivery. *J Control Release.* 2010;148:135-46. DOI: 10.1016/j.jconrel.2010.08.027
 23. Adelsberger J, Kulkarni A, Jain A, Wang W, Bivigou-Koumba AM, Busch P, et al. Thermoresponsive PS-b-PNIPAM-b-PS micelles: aggregation behavior, segmental dynamics, and thermal response. *Macromolecules.* 2010;43:2490-501. DOI: 10.1021/ma902714p
 24. Zhao Y, Fan X, Liu D, Wang Z. PEGylated thermo-sensitive poly (amidoamine) dendritic drug delivery systems. *Int J Pharm.* 2011;409:229-36. DOI: 10.1016/j.ijpharm.2011.02.005
 25. Torchilin VP. Multifunctional, stimuli-sensitive nanoparticulate systems for drug delivery. *Nat Rev Drug Discov.* 2014;13:813-27. DOI: 10.1038/nrd4333
 26. Lal S, Clare SE, Halas NJ. Nanoshell-enabled photothermal cancer therapy: impending clinical impact. *Acc Chem Res.* 2008;41:1842-51. DOI: 10.1021/ar800150g
 27. Guo Q, Zhang T, An J, Wu Z, Zhao Y, Dai X, et al. Block versus Random Amphiphilic Glycopolymer Nanoparticles as Glucose-Responsive Vehicles. *Biomacromolecules.* 2015;16:3345-56. DOI: 10.1021/acs.biomac.5b01020
 28. Wu Q, Wang L, Yu H, Wang J, Chen Z. Organization of glucose-responsive systems and their properties. *Chem Rev.* 2011;111:7855-75. DOI: 10.1021/cr200027j
 29. Gu Z, Aimetti AA, Wang Q, Dang TT, Zhang Y, Veiseh O, et al. Injectable nano-network for glucose-mediated insulin delivery. *ACS Nano.* 2013;7:4194-201. DOI: 10.1021/nn400630x
 30. Yun J, Im JS, Lee Y-S, Kim H-I. Electro-responsive transdermal drug delivery behavior of PVA/PAA/MWCNT nanofibers. *Eur Polym J.* 2011;47:1893-902. DOI: 10.1016/j.eurpolymj.2011.07.024
 31. Ying X, Wang Y, Liang J, Yue J, Xu C, Lu L, et al. Angiogenesis-Conjugated Electro-Responsive Hydrogel Nanoparticles: Therapeutic Potential for Epilepsy. *Angewandte Chemie Int Ed.* 2014;53:12436-40. DOI: 10.1002/anie.201403846
 32. Curcio M, Spizzirri UG, Cirillo G, Vittorio O, Picci N, Nicoletta FP, et al. On demand delivery of ionic drugs from electro-responsive CNT hybrid films. *RSC Advances.* 2015;5:44902-11. DOI: 10.1039/c5ra05484b
 33. Zhang L, Guo R, Yang M, Jiang X, Liu B. Thermo and pH Dual-Responsive Nanoparticles for Anti-Cancer Drug Delivery. *Adv Mater.* 2007;19:2988-92. DOI: 10.1002/adma.200601817
 34. Zhang Z, Wang J, Chen C. Near-Infrared Light-Mediated Nanoplatforams for Cancer Thermo-Chemotherapy and Optical Imaging. *Adv Mater.* 2013;25:3869-80. DOI: 10.1002/adma.201301890
 35. Jochum FD, Theato P. Thermo- and light responsive micellation of azobenzene containing block copolymers. *Chem Communications.* 2010;46:6717-9. DOI: 10.1039/c0cc01288b
 36. Yang F, Hu S, Zhang Y, Cai X, Huang Y, Wang F, et al. A Hydrogen Peroxide-Responsive O₂ Nanogenerator for Ultrasound and Magnetic-Resonance Dual Modality Imaging. *Adv Mater.* 2012;24:5205-11. DOI: 10.1002/adma.201202367
 37. Yang F, Zhang M, He W, Chen P, Cai X, Yang L, et al. Controlled release of Fe₃O₄ nanoparticles in encapsulated microbubbles to tumor cells via sonoporation and associated cellular bioeffects. *Small.* 2011;7:902-10. DOI: 10.1002/sml.201002185
 38. Yang F, Li M, Cui H, Wang T, Chen Z, Song L, et al. Altering the response of intracellular reactive oxygen to magnetic nanoparticles using ultrasound and microbubbles. *Sci Chin Mater.* 2015;58:467-80. DOI: 10.1007/s40843-015-0059-9

39. Cai X, Yang F, Gu N. Applications of magnetic microbubbles for theranostics. *Theranostics*. 2012;2:103-12. DOI: 10.7150/thno.3464
40. Etheridge ML, Campbell SA, Erdman AG, Haynes CL, Wolf SM, McCullough J. The big picture on nanomedicine: the state of investigational and approved nanomedicine products. *Nanomedicine*. 2013;9:1-14. DOI: 10.1016/j.nano.2012.05.013
41. Shaffer SA, Baker-Lee C, Kennedy J, Lai MS, de Vries P, Buhler K, et al. In vitro and in vivo metabolism of paclitaxel polyglumex: identification of metabolites and active proteases. *Cancer Chemother. Pharmacol.* 2007;59:537-48. DOI: 10.1007/s00280-006-0296-4
42. Lindner LH, Hossann M, Vogeser M, Teichert N, Wachholz K, Eibl H, et al. Dual role of hexadecylphosphocholine (miltefosine) in thermosensitive liposomes: active ingredient and mediator of drug release. *J Cont Release*. 2008;125:112-20. DOI: 10.1016/j.jconrel.2007.10.009
43. Gil PR, Hühn D, Loretta L, Sasse D, Parak WJ. Nanopharmacy: Inorganic nanoscale devices as vectors and active compounds. *Pharma Research*. 2010;62:115-25. DOI: 10.1016/j.phrs.2010.01.009
44. Yi Li, Quang Nam Bui, Le Thai Minh Duy, Hong Yu Yang, and Doo Sung Lee. One-Step Preparation of pH-Responsive Polymeric Nanogels as Intelligent Drug Delivery Systems for Tumor Therapy. *Biomacromolecules* **Article ASAP 2018**. DOI: 10.1021/acs.biomac.8b00195. DOI: 10.1021/acs.biomac.8b00195
45. Zhang Y, Xu J. 2018 Mesoporous silica nanoparticle-based intelligent drug delivery system for bienzymeresponsive tumour targeting and controlled release. *R. Soc. open sci.* 2018;5:170986. <http://dx.doi.org/10.1098/rsos.170986>.
46. Zhao H, Li L, Zheng C, Hao Y, Niu M, Hu Y, Chang J, Zhang Z, wang L. An intelligent dual stimuli-responsive photosensitizer delivery system with O₂-supplying for efficient photodynamic therapy. *Coll Surfaces B: Biointerfaces*. Volume 167, Pages 299-309. DOI: 10.1016/j.colsurfb.2018.04.011
47. Li H, Sang Q, Wu J, William GR, Wang H, Niu S, Wu J, Zhu LM. Dual-responsive drug delivery systems prepared by blend electrospinning. *Int J Pharm.* 2018 543(1-2):1-7. DOI: 10.1016/j.ijpharm.2018.03.009
48. Kumar B, Kulanthaivel S, Mondal A, Mishra S, Banerjee B, Bhaumik A, Banerjee I, Giri S. Mesoporous silica nanoparticle based enzyme responsive system for colon specific drug delivery through guar gum capping. *Coll Surfaces B: Biointerfaces*. 2017;150(1):352-361. DOI: 10.1016/j.colsurfb.2016.10.049
49. Yang F, Li M, Liu Y, Wang T, Feng Z, Cui H, et al. Glucose and magnetic-responsive approach toward in situ nitric oxide bubbles controlled generation for hyperglycemia theranostics. *J Cont Release*. 2016;228:87-95. DOI: 10.1016/j.jconrel.2016.03.002
50. Paris JL, Cabañas MV, Manzano M, Vallet-Regí M. Polymer-Grafted Mesoporous Silica Nanoparticles as Ultrasound-Responsive Drug Carriers. *ACS Nano*. 2015;9:11023-33. DOI: 10.1021/acsnano.5b04378
51. Alvarez-Lorenzo C, Concheiro A. Smart drug delivery systems: from fundamentals to the clinic. *Chem Communications*. 2014;50:7743-65. DOI: 10.1039/c4cc01429d
52. Chiang Y-T, Lo C-L. pH-responsive polymer-liposomes for intracellular drug delivery and tumor extracellular matrix switched-on targeted cancer therapy. *Biomaterials*. 2014;35:5414-24. . DOI: 10.1016/j.biomaterials.2014.03.046
53. Kelley EG, Albert JN, Sullivan MO, Epps III TH. Stimuli-responsive copolymer solution and surface assemblies for biomedical applications. *Chem Soc Rev*. 2013;42:7057-71. DOI: 10.1039/c3cs35512h
54. Cheng R, Meng F, Deng C, Klok H-A, Zhong Z. Dual and multi-stimuli responsive polymeric nanoparticles for programmed site-specific drug delivery. *Biomaterials*. 2013;34:3647-57. DOI: 10.1016/j.biomaterials.2013.01.084
55. Duan X, Xiao J, Yin Q, Zhang Z, Yu H, Mao S, et al. Smart pH-sensitive and temporal-controlled polymeric micelles for effective combination therapy of doxorubicin and disulfiram. *ACS Nano*. 2013;7:5858-69. DOI: 10.1021/nn4010796
56. Pan Y-J, Chen Y-Y, Wang D-R, Wei C, Guo J, Lu D-R, et al. Redox/pH dual stimuli-responsive biodegradable nanohydrogels with varying responses to dithiothreitol and glutathione for controlled drug release. *Biomaterials*. 2012;33:6570-9. DOI: 10.1016/j.biomaterials.2012.05.062
57. Mo R, Sun Q, Xue J, Li N, Li W, Zhang C, et al. Multistage pH-Responsive Liposomes for Mitochondrial-Targeted Anticancer Drug Delivery. *Adv Mater*. 2012;24:3659-65. DOI: 10.1002/adma.201201498
58. Leung SJ, Romanowski M. Light-activated content release from liposomes. *Theranostics*. 2012;2:1020-36. DOI: 10.7150/thno.4847
59. Yudina A, De Smet M, Lepetit-Coiffe M, Langereis S, Van Ruysssevelt L, Smirnov P, et al. Ultrasound-mediated intracellular drug delivery using microbubbles and temperature-sensitive liposomes. *J Control Release*. 2011;155:442-8. DOI: 10.1016/j.jconrel.2011.06.006
60. Delcea M, Möhwald H, Skirtach AG. Stimuli-responsive LbL capsules and nanoshells for drug delivery. *Adv Drug Deliv Rev*. 2011;63:730-47. DOI: 10.1016/j.addr.2011.03.010
61. Liu J, Zhang Y, Wang C, Xu R, Chen Z, Gu N. Magnetically sensitive alginate-templated polyelectrolyte multilayer microcapsules for controlled release of doxorubicin. *J Phys Chem*. 2010;114:7673-9. DOI: 10.1021/jp911933b
62. Patel K, Angelos S, Dichtel WR, Coskun A, Yang Y-W, Zink JL, et al. Enzyme-responsive snap-top covered silica nano-

containers. *J Am Chem Soc.* 2008;130:2382-3. DOI: 10.1021/ja0772086

63. Murdan S. Electro-responsive drug delivery from hydrogels. *J Controlled Release.* 2003;92:1-17. DOI: 10.1016/S0168-3659(03)00303-1